



## Technical specifications

Colorex® meets the requirements of EN ISO 10581 and ASTM 1700

		Colorex® SD	Colorex® EC	Colorex® Plus EC	Colorex® Plus Basic	Colorex® Plus R10
		type 1	type 1	type 1	type 1	type 1
	Total thickness	EN ISO 24346	2.0 mm / 3.0 mm*	2.0 mm / 3.0 mm*	10.3 mm	10.3 mm
	Commercial use	EN ISO 10874	34 very heavy	34 very heavy	34 very heavy	34 very heavy
	Light industrial use	EN ISO 10874	43 heavy	43 heavy	43 heavy	43 heavy
	Tile size	EN ISO 24342	615x615 mm 615x1230 mm*	615x615 mm 615x1230 mm*	607x607 mm	607x607 mm
	Total weight	EN ISO 23997	3.2 kg/m <sup>2</sup>	3.2 kg/m <sup>2</sup>	12.0 kg/m <sup>2</sup>	12.0 kg/m <sup>2</sup>
	Electrostatics (general requirements)	IEC 61340-5-1	Compliant	Compliant	Compliant	n.a.
	Electrical resistance	IEC 61340-4-1 ESD STM7.1	1 x 10 <sup>6</sup> ≤ R ≤ 10 <sup>9</sup> Ω	5 x 10 <sup>4</sup> ≤ R ≤ 10 <sup>9</sup> Ω	2.5 x 10 <sup>4</sup> ≤ R ≤ 10 <sup>9</sup> Ω	n.a.
	Electrical resistance in combination with ESD control footwear	IEC 61340-4-5 ESD STM97.1	R ≤ 1 x 10 <sup>9</sup> Ω	R ≤ 3.5 x 10 <sup>9</sup> Ω	R ≤ 3.5 x 10 <sup>9</sup> Ω	n.a.
	Body Voltage Generation, in combination with ESD control footwear <i>Typical value</i>	IEC 61340-4-5 ESD STM97.2	< 100 V ~40 V	< 100 V ~20 V	< 100 V ~20 V	< 2 kV n.a.
	Dimensional stability	EN ISO 23999	≤ 0.05%	≤ 0.05%	≤ 0.25%	≤ 0.25%
	Residual indentation <i>Typical value</i>	EN ISO 24343-1	≤ 0.10 mm ~0.02 mm	≤ 0.10 mm ~0.02 mm	≤ 0.10 mm ~0.05 mm	≤ 0.10 mm ~0.07 mm
	Resistance to loads		Powered pallet truck and forklifts: total weight up to 2.5 t with hard wheels and up to 5 t with air tyres. Static loads: 50 kg/cm <sup>2</sup> - dynamic loads: 90 kg/cm <sup>2</sup> (performance may vary, subject to local conditions)			
	Castor chair continuous use	ISO 4918	pass	pass	pass	pass
	Impact sound reduction	EN ISO 140-8	2 dB	2 dB	12 dB	12 dB
	Light fastness	EN ISO 105-B02	≥ 6	≥ 6	≥ 6	≥ 6
	Resistance to chemicals	EN ISO 26987	Excellent	Excellent	Excellent	Excellent
	Slip resistance	DIN 51130	R9	R9	R9	R10
	Bacteria resistance	ISO 846	Pass	Pass	Pass	Pass
	Thermal dilatation coefficient		0.07 mm/m°C	0.07 mm/m°C	0.07 mm/m°C	0.07 mm/m°C
	Outgassing	IDEMA M11-99	total < 1 µg/cm <sup>2</sup>	total < 1 µg/cm <sup>2</sup>	total < 2 µg/cm <sup>2</sup>	total < 2 µg/cm <sup>2</sup>
	Indoor Air Emissions: TVOC after 28 days	EN 16516	≤ 0.025 mg/m <sup>3</sup>	≤ 0.025 mg/m <sup>3</sup>	≤ 0.025 mg/m <sup>3</sup>	≤ 0.025 mg/m <sup>3</sup>
	Cleanroom particle emission	ISO 14644-1	ISO 4	ISO 2	ISO 2	ISO 4
	<b>Creating better environments</b>					
	Renewable electricity		Colorex SD and Colorex EC are manufactured using 100% electricity from renewable sources			
	Recycled content		Colorex Plus contains up to 95% recycled content in the backing			
			EN 14041 <b>CE</b> 0201083-200P-003	EN 14041 <b>CE</b> 0201083-200P-003	EN 14041 <b>CE</b> 0201083-200P-003	EN 14041 <b>CE</b> 0201079-200P-003
	All Colorex® products meet the requirements of EN 14041					
	Reaction to fire**	EN 13501-1	B <sub>s</sub> -s1, G, CS	B <sub>s</sub> -s1, G, CS	B <sub>s</sub> -s1, L, CS	B <sub>s</sub> -s1, L, CS
	Slip resistance	EN 13893	μ ≥ 0.30	μ ≥ 0.30	μ ≥ 0.30	μ ≥ 0.30
	Thermal conductivity	EN 12524	0.25 W/(m·K)	0.25 W/(m·K)	0.25 W/(m·K)	0.25 W/(m·K)
	Body voltage	EN 1815	≤ 2 kV	≤ 2 kV	≤ 2 kV	≤ 2 kV
	Electrical behaviour - static dissipative	EN 1081	≤ 1 x 10 <sup>9</sup> Ω	n.a.	n.a.	n.a.
	Electrical behaviour - conductive	EN 1081	n.a.	≤ 1 x 10 <sup>9</sup> Ω	≤ 1 x 10 <sup>9</sup> Ω	n.a.

\* Available on request

\*\* Product also tested to ASTM. Fire ASTM E648: class 1, Smoke ASTM 662: pass

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001.

All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001.

The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPDs) which can be found on all of our websites.



# inmind

thinking  
about project



**inmind**

342 Kifisias Ave. & Pindou 58 St.  
15233 Chalandri, Athens

+30 210 6849990  
info@inmind.com.gr

[inmind.com.gr](http://inmind.com.gr)